



TECHNICAL DATA SHEET No 820

SPRAY P340 PLASTOFIX

GENERAL TECHNICAL DESCRIPTION

High-quality aerosol adhesion promoter for plastic parts.

Suitable for metallic substrates as well.

Easy to use.

Fast drying time.

SURFACE

Automotive plastic parts except pure Polyethylene (PE)

HB BODY Polyester Fillers

HB BODY 950 STONE CHIP & U951 AUTOFLEX

Metallic (Stainless steel, Aluminium, Bare steel, Galvanized)

PRETREATMENT/CLEANING OF SUBSTRATE

The surface to be coated must be dry, clean, and free of grease and other contaminants. Ensure all substrates are thoroughly cleaned and dried at every step of the preparation process.



For metallic substrates and polyester fillers, sand substrate with an appropriate grit paper.



Clean the surface with 770 NORMAL / 771 FAST ANTISIL Degreaser.

Use 2 clothes wipe on, wipe off. Always wipe cleaner off the surface as long is wet, with a clean, dry cloth. Remove dust by air blowing and a tack cloth.

PRODUCT APPLICATION:



Shake well before using:
2 - 3 min



Spray at a distance of
20 - 30 cm, thinly applied
coats



2 - 3 coats
20 - 30 µm
(0.8 - 1.2 mil)



5 min / 23°C (73°F)
Flash off time between
coats



10 min / 23°C (73°F)



Overcoat with any
HB BODY Primer and
Topcoat



After use turn bottle
upside down and spray
out a small quantity,
for the cleaning of the
nozzle

SPECIFIC GRAVITY

0.7 ± 0.02 g/cm³

SOLID CONTENT

2.5 ± 0.5% Weight

VOC (2004/42/EC)

This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840g/L. 2004/42/IIB(e)(840)840

REMARKS

- Shake for 2 - 3 min after agitator ball has started to rattle.
- Optimum operating temperature range 10 - 25°C (50 - 77°F).
- Do not use at temperatures below 10°C (50°F).

STORAGE SHELF LIFE

Guaranteed shelf-life 36 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective equipment



Follow the application instructions mentioned in this TDS

The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

JULY 2025